



高能激光 2000W-IPG 光纤激光切割机

GNLASER 2000W-IPG FIBER LASER CUTTING MACHINE

2017 年 3 月版

March-2017 Edition

高能激光 2000W-IPG 光纤激光切割机切割性能

GNLASER 2000W-IPG

FIBER LASER CUTTING MACHINE CUTTING PERFORMANCE TABLE

1. 切割材质及最大厚度

Cutting material and maximum cutting thickness

材质 material	碳钢 carbon steel	不锈钢 stainless steel	铝板 aluminum sheet	铜板 copper sheet
厚度 thickness	18mm	8mm	5mm	5mm

2. 切割材料库

Cutting material storage

碳钢厚度 carbon steel thickness	1mm	2mm	3mm	4mm	5mm	6mm	8mm	10mm	12mm	14mm	16mm	18mm
氧气切割速度 Oxygen cutting speed	250mm /s	100mm /s	50mm /s	43mm /s	37mm /s	33mm /s	18mm /s	17mm /s	16mm/ s	11mm/ s	10mm /s	9mm /s
铝厚度 Aluminium thickness	1mm	2mm	3mm	4mm	5mm							
氮气切割速度 Nitrogen cutting speed	417mm /s	183mm /s	83mm /s	28mm /s	13mm /s							
铜厚度 Copper thickness	1mm	2mm	3mm	4mm	5mm							
氮气切割速度 Nitrogen cutting speed	417mm /s	183mm /s	83mm /s	25mm /s	12mm /s							
不锈钢厚度 Stainless steel thickness	1mm	2mm	3mm	4mm	5mm	6mm	8mm					
氮气切割速度 Nitrogen cutting speed	450mm /s	200mm /s	92mm /s	50mm /s	25mm /s	13mm /s	10mm /s					